SPECIFICATION SHEET

55A6050


29 July 1986

Revision A

CABLE, ELECTRIC, RADIATION-CROSSLINKED, EXTRUDED, MODIFIED, FLUOROPOLYMER-INSULATED, ONE CONDUCTOR, SHIELDED, JACKETED, NORMAL WEIGHT

200°C

The complete requirements for procuring the cable described herein shall consist of this document and the issue in effect of Raychem Specification 55A.



CABLE CONSTRUCTION DETAILS

PART NUMBER	CONDUCTOR SIZE (AWG)	SHIELD SIZE (AWG)	JACKET THICKNESS (inches)		OUTSIDE DIAMETER (inches)		MAXIMUM WEIGHT (lb/1000 ft)
			MINIMUM	NOMINAL 1/	NOMINAL 1/	MAXIMUM	
55A6050-30-*	30	38	.006	.008	.065	.070	4.0
55A6050-28-*	28	38	.006	.008	.068	.073	4.5
55A6050-26-*	26	38	.006	.008	.073	.078	5.3
55A6050-24-*	24	38	.006	.008	.078	.083	6.3
55A6050-22-*	22	38	.006	.008	.084	.089	7.9
55A6050-20-*	20	38	.006	.008	.092	.097	10.0

1/ Nominal values are for information only. Nominal values are not requirements.

CABLE RATINGS AND ADDITIONAL REQUIREMENTS

TEMPERATURE RATING: 200°C
  Maximum continuous conductor temperature
VOLTAGE RATING: 600 volts (rms)
ACCELERATED AGING: 300 ± 3°C for 7 hours
BLOCKING: 200 ± 3°C for 6 hours
DIELECTRIC WITHSTAND: 1500 volts, 60 Hz
FLAMMABILITY:
  Procedure 1, 3 seconds (maximum); 3 in. (maximum); no flaming of facial tissue
JACKET COLOR: White preferred
JACKET ELONGATION AND TENSILE STRENGTH:
  Elongation, 50% (minimum)
  Tensile Strength, 5000 lbf/in^2 (minimum)
JACKET FLAWS:
  Spark Test, 1000 volts, 60 Hz (rms), 100% test
  Impulse Dielectric Test, 6.0 kV (peak), 100% test

LIFE CYCLE: 230 ± 3°C for 500 hours
LOW TEMPERATURE-COLD BEND: -65 ± 2°C for 4 hours
SHIELD COVERAGE: 85% (minimum)
THERMAL SHOCK: 300 ± 3°C for 6 hours
VOLTAGE WITHSTAND TEST: (After Accelerated Aging, Immersion, Life Cycle, Low Temperature-Cold Bend and Thermal Shock) 1000 volts, 60 Hz, 1 minute

PART NUMBER:
  The "*" in the part numbers above shall be replaced by color code designators in accordance with MIL-STD-681 with a dash separating the component wire color from the jacket color.
  Example:
    AWG 20, white component wire, white jacket: 55A6050-20-9-9.

HIS SPECIFICATION SHEET TAKES PRECEDENCE OVER DOCUMENTS REFERENCED HEREIN.
EFERENCED DOCUMENTS SHALL BE OF THE ISSUE IN EFFECT ON DATE OF INVITATION FOR BID.

Raychem
Raychem Corporation
300 Constitution Drive, Menlo Park, California 94
415) 361 3333 TWX 910 373 1205